

PROGUARD CN 100 ISO

Coat for Every Industry!

PRODUCT DESCRIPTION:

PROGUARD CN 100 ISO is a two pack special composite coating containing micro-ceramic particles reinforcement, based on an ultra modern Novolac-resin base, providing chemical resistance, corrosion and abrasion protection to a wide variety of substrates in extremely aggressive environments at elevated temperatures.

APPLICATION DATA:

Application methods:

Airless spray pump (without filter), Ratio 1:68 or greater. Tip size: 0.019-0.029"; Hose length max. 20m; Spray hose diameter max. 1"; Material must be taken up directly (without intake hose); avoid waiting time under pressure (reduction of pot life!)

Mixing ratio:

9 : 1 by weight

Mixing time:

Component A – premix 4 minutes; then Components A+B – mix 2 minutes; Mixer cycles >100rpm

Potlife (23°C):

30-40 minutes (reduced at higher temperatures)

Material Spray Temp:

Min. 20°C

Thinner:

Thinners should not be added. Proguard thinners should be used to clean and flush equipment

Filters:

Remove filters

Number of Coats:

1 or 2 coats - depending on environment. Minimum coating thickness 500µm. Maximum thickness per layer: 1,0 mm

TECHNICAL INFORMATION:

Colour:

Light Grey, Dark Grey

Volume Solids:

100%

VOC:

0 mg

Flexibility:

Excellent

Surface:

Mat

Chemical resistance

Excellent (see Resistance List)

Abrasion resistance:

80 mg (ASTM D 4060)

Adhesion:

> 27 N/mm² (ISO 4624)

Specific Gravity (Mix):

1,10

Application range:

| Film thickness per coat | | Theoretical consumption kg/m ² |
|-------------------------|---------|---|
| Dry | Wet | |
| 1000 µm | 1000 µm | 1,50 |
| 2000 µm | 2000 µm | 3,00 |

SURFACE PREPARATION:

Gritblasting to minimum Sa 2,5 (ISO 8501-1). Surface must have a good coarse profile with an average roughness of 80-100 µm.

CONDITION DURING APPLICATION:

Substrate temperature **must** be above 15°C and at least 5°C above dew point. Relative humidity **should** be below 85%. Temperature and relative humidity must be measured in the vicinity of the substrate.

DRYING TIME:

| Substrate temperature | Fully cured | Chemically resistant | Recoating time (wet-on wet) | |
|-----------------------|-------------|----------------------|-----------------------------|---------|
| | | | Minimum | Maximum |
| 23°C | 48 h* | 7 d | 10 h | 24 h |

STORAGE AND PACKING:

Preferred storage conditions are to keep the containers in a dry and cool area below 35°C provided with adequate ventilation. The containers should be sealed tightly.

Packing:

15,0 KG-kits including hardener (13,5 kg-A + 1,5 kg-B)

Shelf life:

See labels for shelf life details

QUALITY ASSURANCE AND INSPECTION:

To ensure a continuous quality of the products, quality assurance and inspection plan of the material manufacturer has to be considered. For the porosity test is just a sponge-tester permitted. The test voltage has to be 90 V. Recommendations for qualified test control units are available at the manufacturer.

HEALTH AND SAFETY:

Observe the precautionary notices on the container label, and read the Material Safety Data Sheet before use. The product is intended for use by properly qualified professional applicators in industrial conditions. The product is flammable and should be kept away from sparks, open flames, and other sources of ignition. Smoking is prohibited in the application area. Wear suitable respiratory equipment and apply in well ventilated areas. Avoid contact with skin and eyes.

Disclaimer:

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we can not guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.